

Material

45 NBR 670

Revision Index
06

Revision Date
10.10.2018

General Data

Colour: black
 Type of cross-linking: Sulfur

Physical Properties

	Nominal Range	Typical Value	
Density DIN EN ISO 1183-1		1.14	g/cm ³
Hardness DIN ISO 7619-1	45 ±5	43	Shore
Rebound resilience DIN 53512		45	%
Modulus 100 %, DIN 53504, S2	>0.5	1.1	MPa
Tensile strength DIN 53504, S2	>7	9.5	MPa
Elongation at break DIN 53504, S2	>600	980	%
Compression set DIN ISO 815, 22 h, 100 °C		40	%

The given values are based on a limited number of tests on standard test pieces (2mm sheets) produced in the laboratory. The data from finished parts can deviate from above values depending on the manufacturing process and the component geometry. The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

Print date: 30.04.2025