

Material

45 NBR 670

black

cross linking: sulfur

revision index
6

revision date
10/10/2018

page 1 / 2

Physical properties

	nominal range	typical values	
Density DIN EN ISO 1183-1	---	1.14	g/cm ³
Hardness DIN ISO 7619-1	45 ±5	43	Shore
Rebound resilience DIN 53512	---	45	%
Modulus 100 %, DIN 53504, S2	> 0.5	1.1	MPa
Tensile strength DIN 53504, S2	> 7	9.5	MPa
Elongation at break DIN 53504, S2	> 600	980	%
Compression set DIN ISO 815, 22 h, 100 °C	---	40	%

Declarations of conformity
No data found!

Freudenberg

Freudenberg FST GmbH
Technology&Innovation
Material Compliance

Telefon: -

Fax: -

Email: MaterialCompliance@fst.com

Material

45 NBR 670

black

cross linking: sulfur

revision index

6

revision date

10/10/2018

page

2 / 2

Tested after ASTM D 2000: M 5 BG 507 A14 B14 EO14 EO34

		nominal range	typical values
Hardness	Shore	50 ±5	43
Tensile strength	MPa	min. 7	9.6
Elongation at break	%	min. 350	970
A14 Change after aging in Air 70h/100°C			
Hardness	Shore A	±15	4
Tensile strength	%	-20	14
Elongation at break	%	-40	-18
B14 Compression set 22h/100°C			
	%	25	34
EO14 Change after aging in IRM 901 70h/100°C			
Hardness	Shore A	-5 to 15	10
Tensile strength	%	-25	23
Elongation at break	%	-45	-13
Volume	%	-10 to 5	-12
EO34 Change after aging in IRM 903 70h/100°C			
Hardness	Shore A	0 to -15	-1
Tensile strength	%	-45	-3
Elongation at break	%	-45	-5
Volume	%	0 to 35	2

The given values are based on a limited number of tests on standard test pieces (2mm sheets) produced in the laboratory. The data from finished parts can deviate from above values depending on the manufactories process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

Freudenberg

Freudenberg FST GmbH

Technology&Innovation

Material Compliance

Telefon: -

Fax: -

Email: MaterialCompliance@fst.com