

Material

50 NBR 253

black

cross linking: sulfur

Attention! Not for new samples

revision index

9

revision date

12/23/2010

page

1 / 3

Not for new samples. possible replacement material:

50 NBR 216214

Physical properties

	nominal range	typical values	
Density DIN EN ISO 1183-1	1.11 ±0.02	1.11	g/cm ³
Hardness DIN ISO 7619-1	50 ±5	50	Shore
Rebound resilience DIN 53512	---	39	%
Modulus 100 %, DIN 53504, S2	> 0.8	1.2	MPa
Tensile strength DIN 53504, S2	> 11	14.8	MPa
Elongation at break DIN 53504, S2	> 500	620	%
Compression set DIN ISO 815, 22 h, 100 °C	< 35	25	%
Temperature range	-45°C to 80°C		

Declarations of conformity

This overview is purely informative and does not constitute a declaration of conformity (DoC). Please refer to the actual declaration of conformity (DoC) including the conditions and its validity period.

Country	Part	Remark	Expires
Info ROHS and ELV		EU 2000/53 (ELV) including EU 2011/65 and EU2015/863 (ROHS III)	see DoC

Freudenberg

Freudenberg FST GmbH
Technology&Innovation
Material Compliance

Telefon: -

Fax: -

Email: MaterialCompliance@fst.com

Material

50 NBR 253

black

cross linking: sulfur

Attention! Not for new samples

revision index

9

revision date

12/23/2010

page

2 / 3

Tested after ASTM D 2000: M 5 BG 510 A14 B14 B34 EO14 EO34 F19

		nominal range	typical values
Hardness	Shore	50 ±5	49
Tensile strength	MPa	min. 10	14.1
Elongation at break	%	min. 300	530
A14 Change after aging in Air 70h/100°C			
Hardness	Shore A	±15	7
Tensile strength	%	-20	-7
Elongation at break	%	-40	-25
B14 Compression set 22h/100°C	%	25	11
B34 Compression set 22h/100°C	%	25	14
EO14 Change after aging in IRM 901 70h/100°C			
Hardness	Shore A	-5 to 15	5
Tensile strength	%	-25	10
Elongation at break	%	-45	-20
Volume	%	-10 to 5	-6
EO34 Change after aging in IRM 903 70h/100°C			
Hardness	Shore A	0 to -15	-19
Tensile strength	%	-45	-40
Elongation at break	%	-45	-40
Volume	%	0 to 35	48
F19 Low-temperature resistance after 3 min at -55 °C 3min./-55°C		pass	

Surface resistance R_o according to DIN IEC 93 / VDE 0303 part 30: 5,2 x 10⁵

Freudenberg

Freudenberg FST GmbH

Technology&Innovation

Material Compliance

Telefon: -

Fax: -

Email: MaterialCompliance@fst.com

Material

50 NBR 253

black

cross linking: sulfur

Attention! Not for new samples

revision index	revision date	page
9	12/23/2010	3 / 3

The given values are based on a limited number of tests on standard test pieces (2mm sheets) produced in the laboratory. The data from finished parts can deviate from above values depending on the manufactories process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisons do not plan for something else.

Freudenberg

Freudenberg FST GmbH

Technology&Innovation

Material Compliance

Telefon: -

Fax: -

Email: MaterialCompliance@fst.com