

Material 53 CR 858

				9
revision index	revision date			
1	3/3/2005		pa	ge 1/2
Physical properties		nominal range	typical values	
Density DIN EN ISO 1183-1		1 43 ±0.02	1.43	g/cm³
Hardness DIN ISO 7619-1		53 15	5 5	Shore
Rebound resilience DIN 53512		90.96	45	%
Modulus 100 %, DIN 53504, S2	3	0 00	2.2	MPa
Tensile strength DIN 53504, S2	0.4	>11	15.7	MPa
Elongation at break DIN 53504, S2	1 1 1 C	> 300	380	%
Compression set DIN ISO 815, 22 h, 100 °C			25	%
Low Temperature DIN 53765, DSC	01,91		-48	°C
Declarations of conformity				

This overview is purely informative and does not constitute a declaration of conformity (DoC). Please refer to the actual declaration of conformity (DoC) including the conditions and its validity period.

Info ROHS and ELV

Remark

EU 2000/53 (ELV) including EU 2011/65 and EU2015/863 (ROHS III)

Remark

EU 2000/53 (ELV) including EU 2011/65 and EU2015/863 (ROHS III)

Freudenberg

Freudenberg FST GmbH Technology&Innovation Material Compliance

Telefon: -Fax: -

Email: MaterialCompliance@fst.com



Material 53 CR 858

revision index revision date 3/3/2005

No ASTM D2000 properties available

This material contains a SVHC-substance <0,1% (Imidazolidin-2-thio No. 96-45-7) in the vulcanized parts.

The given values are based on a limited number of tests on standard test pieces (2mm/sheets) produced in the laboratory. The data from finished parts can deviate from above values depending on the manufactories process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the quarantee of this product are in line with our terms and conditions, inasmuch as statutory provisons do not plan for something else.



Freudenberg

Freudenberg FST GmbH Technology&Innovation Material Compliance

Telefon: -Fax:

Email: MaterialCompliance@fst.com