

Material
60 NBR 889

black

cross linking: sulfur

revision index
2

revision date
8/5/2011

page 1 / 2

Physical properties

	nominal range	typical values	
Density DIN EN ISO 1183-1	1.14 ±0.02	1.14	g/cm ³
Hardness DIN ISO 7619-1	60 ±5	63	Shore
Rebound resilience DIN 53512	---	50	%
Modulus 100 %, DIN 53504, S2	> 2.5	4.2	MPa
Tensile strength DIN 53504, S2	> 7	9.6	MPa
Elongation at break DIN 53504, S2	> 170	205	%
Tear strength DIN ISO 34-1, B, 23 °C	> 5	8	KN/m
Compression set DIN ISO 815, 22 h, 100 °C	< 30	20	%

Declarations of conformity
No data found!

Freudenberg

Freudenberg FST GmbH
Technology&Innovation
Material Compliance

Telefon: -

Fax: -

Email: MaterialCompliance@fst.com

Material

60 NBR 889

black

cross linking: sulfur

revision index	revision date	page	2 / 2
2	8/5/2011		

Tested after ASTM D 2000: M 2 BF 608 B14 B34 EO14 EO34 F19 Z1

		nominal range	typical values
Hardness	Shore	60 ±5	64
Tensile strength	MPa	min. 8	9.5
Elongation at break	%	min. 250	200
B14 Compression set 22h/100°C	%	25	12
B34 Compression set 22h/100°C	%	25	14
EO14 Change after aging in IRM 901 70h/100°C			
Hardness	Shore	±10	7
Tensile strength	%	-25	16
Elongation at break	%	-45	-5
Volume	%	±10	-13
EO34 Change after aging in IRM 903 70h/100°C			
Hardness	Shore	-20	-6
Tensile strength	%	-45	-11
Elongation at break	%	-45	-19
Volume	%	0 to 60	15
F19 Low-temperature resistance after 3 min at -55 °C 3min./-55°C		pass	
Z1 Elongation at break DIN 53504, S2, 23 °C, längs	%	---	200

Temperature-range: - 50 °C to +80 °C

The given values are based on a limited number of tests on standard test pieces (2mm sheets) produced in the laboratory. The data from finished parts can deviate from above values depending on the manufactories process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

Freudenberg

Freudenberg FST GmbH
 Technology&Innovation
 Material Compliance
 Telefon: -
 Fax: -
 Email: MaterialCompliance@fst.com