

Technical data sheet in accordance with ASTM

Material

60 NBR N604W

black

cross linking: sulfur

revision index

1

revision date

9/21/2021

page

1 / 3

Physical properties

	nominal range	typical values	
Density ASTM D297	1.21 ±0.02	1.21	g/cm ³
Hardness ASTM D 2240, Shore A	60 ±5	59	Shore
Modulus 100 %, ASTM D412, C	---	378	Psi
Tensile strength ASTM D412, C	> 1450	2163	Psi
Elongation at break ASTM D 412	> 300	444	%
Compression set ASTM D395, Slab B, 22 h, 100 °C	< 25	22	%

Declarations of conformity

No data found!

Freudenberg

Freudenberg FST GmbH
Technology&Innovation
Material Compliance

Telefon: -

Fax: -

Email: MaterialCompliance@fst.com

Technical data sheet in accordance with ASTM

Material

60 NBR N604W

black

cross linking: sulfur

revision index

1

revision date

9/21/2021

page

2 / 3

Tested after ASTM D 2000: M 2 BG 610 B14 EF11 EF21 Z1 Z2

		nominal range	typical values
Hardness	Shore	60 ±5	59
Tensile strength	MPa	min. 10	14.92
Elongation at break	%	min. 300	444
A14 Change after aging in Air 70h/100°C			
Hardness	Shore A	---	4
Tensile strength	%	---	5
Elongation at break	%	---	-19
B14 Compression set 22h/100°C			
	%	25	22
EF11 Change after aging in Fuel A 70h/23°C			
Hardness	Shore A	±10	-1
Tensile strength	%	-25	-16
Elongation at break	%	-25	-11
Volume	%	-5 to 10	3.5
EF21 Change after aging in Fuel B 70h/23°C			
Hardness	Shore A	0 to -30	-13
Tensile strength	%	-60	-40
Elongation at break	%	-60	-41
Volume	%	0 to 40	23.5
Z1 Modulus 100 %, DIN 53504, S2, 23 °C			
	MPa	---	2.61
Z2 Density DIN EN ISO 1183-1, 20 °C			
	g/cm ³	---	1.21

The given values are based on a limited number of tests on standard test pieces (2mm sheets). The data from finished parts can deviate from above values depending on the manufacturing process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its

Freudenberg

Freudenberg FST GmbH

Technology&Innovation

Material Compliance

Telefon: -

Fax: -

Email: MaterialCompliance@fst.com

Technical data sheet in accordance with ASTM

Material

60 NBR N604W

black

cross linking: sulfur

revision index

1

revision date

9/21/2021

page 3 / 3

intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

Freudenberg

Freudenberg FST GmbH
Technology&Innovation
Material Compliance

Telefon: -

Fax: -

Email: MaterialCompliance@fst.com