

Material
60 VMQ 117117

transparent

cross linking: peroxidic

revision index	revision date	page	1 / 2
4	11/20/2012		

Physical properties	nominal range	typical values	
Density DIN EN ISO 1183-1	1.17 ±0.02	1.17	g/cm ³
Hardness DIN ISO 7619-1	60 ±5	60	Shore
Rebound resilience DIN 53512	> 20	30	%
Modulus 100 %, DIN 53504, S2	---	2.4	MPa
Tensile strength DIN 53504, S2	> 7	8.8	MPa
Elongation at break DIN 53504, S2	> 320	450	%
Compression set DIN ISO 815, 22 h, 175 °C	< 30	25	%
Temperature range	-50°C to 200°C		

Declarations of conformity

This overview is purely informative and does not constitute a declaration of conformity (DoC). Please refer to the actual declaration of conformity (DoC) including the conditions and its validity period.

	Country	Part	Remark	Expires
(EG) 1935/2004	EU		food	see DoC
(EG) 2023/2006 (GMP)	EU		(EG) 2023/2006 (GMP)	see DoC
ADI Free			see certificate	see DoC
BfR XV	DE		BfR XV	see DoC
BPA/Phthalate free			BPA/Phthalate free	see DoC
FDA	USA	Seals	§ 177.2600	see DoC
GB 4806.11 / 9685	CN	Seals		see DoC
Info ROHS and ELV			EU 2000/53 (ELV) including EU 2011/65 and EU2015/863 (ROHS III)	see DoC

Freudenberg
Freudenberg FST GmbH
Technology&Innovation
Material Compliance

Telefon: -
Fax: -
Email: MaterialCompliance@fst.com



Material

60 VMQ 117117

transparent

cross linking: peroxidic

revision index

4

revision date

11/20/2012

page 2 / 2

No ASTM D2000 properties available

Specific characteristic and limitations for the use in food contact are set out in the corresponding declaration of conformities.

The given values are based on a limited number of tests on standard test pieces (2mm sheets) produced in the laboratory. The data from finished parts can deviate from above values depending on the manufactories process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

Freudenberg

Freudenberg FST GmbH
Technology&Innovation
Material Compliance

Telefon: -
Fax: -
Email: MaterialCompliance@fst.com

