

## Material

### 70 AU 6865

**Revision Index**  
03**Revision Date**  
28.10.2022**Physical Properties**

	<b>Nominal Range</b>	<b>Typical Value</b>	
<b>Density</b> ASTM D297		1.15	g/cm <sup>3</sup>
<b>Hardness</b> ASTM D2240, Shore A	70 ±5	70	Shore
<b>Modulus</b> 100 %, ASTM D412, C		550	psi
<b>Tensile strength</b> ASTM D412, C	>4000	5000.0	psi
<b>Elongation at break</b> ASTM D412, C	>600	600	%
<b>Compression set</b> ASTM D395, B, 70 h, 70 °C, 25 %	<18	12	%
<b>Glass transition temperature</b> DIN EN ISO 11357-2, DSC		-39	°C

The given values are based on a limited number of tests on standard test pieces (2mm sheets) produced in the laboratory. The data from finished parts can deviate from above values depending on the manufacturing process and the component geometry. The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

**Print date:** 23.06.2025