

Material

70 EPDM 291

Revision Index
 07

Revision Date
 15.05.2024

General Data

 Colour: black
 Type of cross-linking: Peroxidic

Declaration of Compliance for - Food & Beverage - Pharmaceutical is available upon request for selected articles. Please contact your known sales contact or send an email to info@fst.com.

Physical Properties

	Nominal Range	Typical Value	
Density DIN EN ISO 1183-1, 23 °C	1.09 ±0.02	1.09	g/cm³
Hardness DIN ISO 48-4, Shore A, 23 °C	75 ±5	79	Shore
Modulus 100 %, DIN 53504, S2, 23 °C	>8	10.8	MPa
Tensile strength DIN 53504, S2, 23 °C	>14	16	MPa
Elongation at break DIN 53504, S2, 23 °C	>150	160	%
Compression set DIN ISO 815, B, 24 h, 150 °C, 25 %	<20	11	%
Glass transition temperature ISO 11357-2, DSC	<-48	-53	°C
Low temperature ISO 2921, TR10	<-44	-47	°C

Temperature Range

 static: -50 to 150 °C
 dynamic: -40 to 150 °C

The given values are based on a limited number of tests on standard test pieces (2mm sheets) produced in the laboratory. The data from finished parts can deviate from above values depending on the manufacturing process and the component geometry. The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

Print date: 29.04.2025
