

Material

70 FKM FP701806

Revision Index
01

Revision Date
03.07.2017

General Data

Colour: black
 Type of cross-linking: Bisphenol cure system

Physical Properties	Nominal Range	Typical Value	
Density ASTM 1817	1.99 ±0.03	1.99	g/cm ³
Hardness ASTM D2240, Shore A	70 ±5	70	Shore
Tensile strength ASTM D412		13.5	MPa
Elongation at break ASTM D412		236	%
Low temperature resistance ASTM D 2137, 3 min, pass		-25	°C
Compression set ASTM D395, B, 22 h, 200 °C		24.7	%
Low temperature ASTM D1329, TR10		-17.3	°C

The given values are based on a limited number of tests on standard test pieces (2mm sheets) produced in the laboratory. The data from finished parts can deviate from above values depending on the manufacturing process and the component geometry. The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

Print date: 29.04.2025