

Material

70 NBR B276

Revision Index
 08

Revision Date
 30.09.2022

General Data

Colour: black

Physical Properties

	Nominal Range	Typical Value	
Hardness DIN ISO 7619-1, Shore A, 23 °C	70 ±5	70	Shore
Hardness DIN ISO 7619-1, IRHD, 23 °C	70 ±5	72	Shore
Tensile strength DIN 53504, S2, 23 °C	>12	16	MPa
Elongation at break DIN 53504, S2, 23 °C	>250	340	%
Modulus 100 %, DIN 53504, S2, 23 °C		4.8	MPa
Tear strength DIN 53507, A, 23 °C		19.4	KN/m
Compression set DIN ISO 815, B, 22 h, 70 °C, 25 %	<10	5.8	%
Compression set DIN ISO 815, B, 70 h, 100 °C, 25 %	<18	16	%
Glass transition temperature ISO 11357-2, DSC			°C
ACN-Content			%

Temperature Range

static: -30 to 100 °C

The given values are based on a limited number of tests on standard test pieces (2mm sheets) produced in the laboratory. The data from finished parts can deviate from above values depending on the manufacturing process and the component geometry. The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

Print date: 29.04.2025