

Material

70 NBR N7013Z

Revision Index
01

Revision Date
01.10.2021

General Data

Colour: black
 Type of cross-linking: Sulfur

Physical Properties

	Nominal Range	Typical Value	
Density ASTM D 1817		1.252	g/cm ³
Hardness ASTM D 2240, Shore A	70 ±5	73.5	Shore
Tensile strength ASTM D 412	>14	16.11	MPa
Elongation at break ASTM D 412	>250	272	%
Modulus 100 %, ASTM D412		5.87	MPa
Modulus 200 %, ASTM D412		12.67	MPa
Tear strength ASTM D624, C		47.07	KN/m
Low temperature ASTM D 1329, TR10		-30	°C
Compression set ASTM D 395, B, 22 h, 100 °C	<25	9	%

The given values are based on a limited number of tests on standard test pieces (2mm sheets) produced in the laboratory. The data from finished parts can deviate from above values depending on the manufactories process and the component geometry. The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

Print date: 29.04.2025