

Material

70 NBR NB703413

Revision Index
06

Revision Date
12.04.2024

General Data

Colour: green
 Type of cross-linking: Sulfur

Physical Properties

	Nominal Range	Typical Value	
Density ASTM D297	1.47 ±0.02	1.47	g/cm ³
Hardness ASTM D2240, Shore A	70 ±5	71	Shore
Tensile strength ASTM D412		14.8	MPa
Elongation at break ASTM D412		405	%
Compression set ASTM D395, 22 h, 100 °C		10	%

Temperature Range

static: -40 to 100 °C

The given values are based on a limited number of tests on standard test pieces (2mm sheets) produced in the laboratory. The data from finished parts can deviate from above values depending on the manufactories process and the component geometry. The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

Print date: 29.04.2025