

Material

70 NBR NB704604

Revision Index
03

Revision Date
09.09.2022

General Data

Colour: black
 Type of cross-linking: Sulfur

Physical Properties

	Nominal Range	Typical Value	
Density ASTM D 1817	1.25 ±0.02	1.26	g/cm ³
Hardness ASTM D2240, Shore A	70 ±5	72	Shore
Tensile strength ASTM D412		18.4	MPa
Elongation at break ASTM D412		341	%
Modulus 100 %, ASTM D412		4.6	MPa
Compression set ASTM D 395, B, 22 h, 100 °C		9	%

Temperature Range

static: -25 to 100 °C

The given values are based on a limited number of tests on standard test pieces (2mm sheets) produced in the laboratory. The data from finished parts can deviate from above values depending on the manufacturing process and the component geometry. The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

Print date: 29.04.2025