

Material

70 VMQ P4OR71VM

Revision Index
04

Revision Date
03.02.2025

General Data

Colour: auburn
Type of cross-linking: Peroxidic

Physical Properties

	Nominal Range	Typical Value
Hardness DIN ISO 7619-1, Shore A	70 ±5	Shore
Tensile strength ISO 37	>6	MPa
Elongation at break ISO 37	>150	%
Low temperature ISO 2921, TR10	<-40	°C
Compression set DIN ISO 815, B, 72 h, 175 °C	<35	%

Temperature Range

static: -55 to 200 °C

The nominal ranges listed in this document are based on the ISO 3601-5 Standard (Fluid power systems - O-rings - Specification of elastomeric materials for industrial applications).

The given values are based on a limited number of tests on standard test pieces (2mm sheets) produced in the laboratory. The data from finished parts can deviate from above values depending on the manufacturing process and the component geometry. The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

Print date: 29.04.2025