

Technical data sheet in accordance with ASTM

Material

70 AU 6865

revision index	revision date	page	1 / 2
2	10/28/2022		

Physical properties	nominal range	typical values	
Density ASTM D297	---	1.15	g/cm ³
Hardness ASTM D2240, Shore A	70 ±5	70	Shore
Modulus 100 %, ASTM D412, C	---	650	Psi
Tensile strength ASTM D412, C	> 4000	4543	Psi
Elongation at break ASTM D412, C	> 600	725	%
Compression set ASTM D395, Slab B, 70 h, 70 °C, 25 %	< 18	12	%

Declarations of conformity
No data found!

Technical data sheet in accordance with ASTM

Material

70 AU 6865

revision index

2

revision date

10/28/2022

page

2 / 2

No ASTM D2000 properties available

The given values are based on a limited number of tests on standard test pieces (2mm sheets). The data from finished parts can deviate from above values depending on the manufacturing process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

Freudenberg

Freudenberg FST GmbH

Technology&Innovation

Material Compliance

Telefon: -

Fax: -

Email: MaterialCompliance@fst.com