

Material

70 EPDM 253815

white

cross linking: peroxidic

revision index

3

revision date

11/10/2010

page

1 / 2

Physical properties

	nominal range	typical values	
Density DIN EN ISO 1183-1, 23 °C	1.10 ±0.02	1.10	g/cm ³
Hardness DIN ISO 7619-1, Shore A, 23 °C	70 ±5	72	Shore
Modulus 100 %, DIN 53504, S2, 23 °C	---	---	MPa
Tensile strength DIN 53504, S2, 23 °C	> 10	17.4	MPa
Elongation at break DIN 53504, S2, 23 °C	> 140	391	%
Compression set DIN ISO 815, Slab B, 24 h, 150 °C, 25 %	< 30	26	%

Temperature range

-40°C to 150°C

Declarations of conformity

This overview is purely informative and does not constitute a declaration of conformity (DoC). Please refer to the actual declaration of conformity (DoC) including the conditions and its validity period.

	Country	Part	Remark	Expires
(EG) 1935/2004	EU		food	see DoC
(EG) 2023/2006 (GMP)	EU		(EG) 2023/2006 (GMP)	see DoC
ADI Free			see certificate	see DoC
BFR XXI, Kat 4	DE		food	see DoC
BPA/Phthalate free			BPA/Phthalate free	see DoC
Cytotoxicity USP chapter 87 & 88 (class VI)	-	Seals		03 / 2033
FDA	USA	Seals	§ 177.2600	see DoC

Freudenberg

Freudenberg FST GmbH
Technology&Innovation
Material Compliance

Telefon: -
Fax: -
Email: MaterialCompliance@fst.com



Material

70 EPDM 253815

white

cross linking: peroxidic

revision index

3

revision date

11/10/2010

page 2 / 2

No ASTM D2000 properties available

The given values are based on a limited number of tests on standard test pieces (2mm sheets) produced in the laboratory. The data from finished parts can deviate from above values depending on the manufactories process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

Freudenberg

Freudenberg FST GmbH
Technology&Innovation
Material Compliance

Telefon: -
Fax: -
Email: MaterialCompliance@fst.com

