

Material

70 NBR 150

black

cross linking: peroxidic

revision index
22

revision date
6/27/2016

page 1 / 4

Physical properties

	nominal range	typical values	
Density DIN EN ISO 1183-1	1.17 ±0.02	1.17	g/cm ³
Hardness DIN ISO 7619-1	70 ±5	72	Shore
Rebound resilience DIN 53512	> 20	28	%
Modulus 100 %, DIN 53504, S2	> 4	5.5	MPa
Tensile strength DIN 53504, S2	> 15	18.5	MPa
Elongation at break DIN 53504, S2	> 180	240	%
Compression set DIN ISO 815, Slab B, 22 h, 100 °C	< 20	12	%
Tear strength DIN 53515, Winkel	---	10	KN/m
Low Temperature ISO 11357-2, DSC	---	-24	°C
Temperature range	-20°C to 100°C		

Declarations of conformity

This overview is purely informative and does not constitute a declaration of conformity (DoC). Please refer to the actual declaration of conformity (DoC) including the conditions and its validity period.

	Country	Part	Remark	Expires
ADI Free DVGW Baumusterprüfzertifikat Gas Info ROHS and ELV	D	Seals	see certificate DIN EN 549 H3 B1 EU 2000/53 (ELV) including EU 2011/65 and EU2015/863 (ROHS III)	see DoC 09 / 2025 see DoC

Freudenberg

Freudenberg FST GmbH
Technology&Innovation
Material Compliance

Telefon: -
Fax: -
Email: MaterialCompliance@fst.com



Material **70 NBR 150**

black

cross linking: peroxidic

revision index
22

revision date
6/27/2016

page 2 / 4

Freudenberg

Freudenberg FST GmbH
Technology&Innovation
Material Compliance

Telefon: -
Fax: -
Email: MaterialCompliance@fst.com



Material

70 NBR 150

black

cross linking: peroxidic

revision index
22

revision date
6/27/2016

page 3 / 4

Tested after ASTM D 2000: M 2 BG 714 B14 B34 EA14 EF11 EF21 EO14 EO34

		nominal range	typical values
Hardness	Shore	70 ±5	70
Tensile strength	MPa	min. 14	17.5
Elongation at break	%	min. 250	290
A14 Change after aging in Air 70h/100°C			
Hardness	Shore A	---	4
Tensile strength	%	---	4
Elongation at break	%	---	-19
B14 Compression set 22h/100°C	%	25	7
B34 Compression set 22h/100°C	%	25	8
EA14 Change after aging in Distilled water 70h/100°C			
Hardness	Shore A	±10	-1
Volume	%	±15	3
EF11 Change after aging in Fuel A 70h/23°C			
Hardness	Shore A	±10	5
Tensile strength	%	-25	-20
Elongation at break	%	-25	-15
Volume	%	-5 to 10	0.2
EF21 Change after aging in Fuel B 70h/23°C			
Hardness	Shore A	0 to -30	-12
Tensile strength	%	-60	-55
Elongation at break	%	-60	-50
Volume	%	0 to 40	30

Freudenberg

Freudenberg FST GmbH
Technology&Innovation
Material Compliance

Telefon: -
Fax: -
Email: MaterialCompliance@fst.com



Material

70 NBR 150

black

cross linking: peroxidic

revision index

22

revision date

6/27/2016

page

4 / 4

EO14 Change after aging in IRM 901 70h/100°C

Hardness	Shore A	-5 to 10	3
Tensile strength	%	-25	-2
Elongation at break	%	-45	-10
Volume	%	-10 to 5	-3

EO34 Change after aging in IRM 903 70h/100°C

Hardness	Shore A	-10 to 5	-3
Tensile strength	%	-45	-7
Elongation at break	%	-45	-14
Volume	%	0 to 25	10 ±5

The given values are based on a limited number of tests on standard test pieces (2mm sheets) produced in the laboratory. The data from finished parts can deviate from above values depending on the manufacturing process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

Freudenberg

Freudenberg FST GmbH
Technology&Innovation
Material Compliance

Telefon: -
Fax: -
Email: MaterialCompliance@fst.com

