

Technical data sheet in accordance with ASTM

Material

70 NBR 3105

black

revision index

1

revision date

4/29/2022

page

1 / 2

Physical properties

typical values

Density

ASTM D297

1.27

g/cm³

Hardness

ASTM D2240, Shore A

70

Shore

Modulus

100 %, ASTM D412, C

796

Psi

Tensile strength

ASTM D412, C

2005

Psi

Elongation at break

ASTM D412, C

217

%

Compression set

ASTM D395, Slab B, 22 h, 100 °C

7.8

%

Compression set

ASTM D395, Slab B, 70 h, 125 °C

22.1

%

Declarations of conformity

No data found!

Freudenberg

Freudenberg FST GmbH

Technology&Innovation

Material Compliance

Telefon: -

Fax: -

Email: MaterialCompliance@fst.com

Technical data sheet in accordance with ASTM

Material

70 NBR 3105

black

revision index

1

revision date

4/29/2022

page 2 / 2

No ASTM D2000 properties available

The given values are based on a limited number of tests on standard test pieces (2mm sheets). The data from finished parts can deviate from above values depending on the manufacturing process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

Freudenberg

Freudenberg FST GmbH

Technology&Innovation

Material Compliance

Telefon: -

Fax: -

Email: MaterialCompliance@fst.com