

Technical data sheet in accordance with ASTM

Material

70 NBR 99006

revision index
3

revision date
5/4/2021

page 1 / 3

Physical properties

	nominal range	typical values	
Density ASTM D297	1.28 ±0.02	1.28	g/cm ³
Hardness ASTM D2240, Shore A	70 ±5	71	Shore
Tensile strength ASTM D412	> 10	18.5	MPa
Elongation at break ASTM D412	> 250	589	%
Glass Transition Temperature ASTM E1356-03	---	-20	°C
Compression set ASTM D395, Slab B, 22 h, 100 °C	---	22	%

Declarations of conformity
No data found!

Freudenberg

Freudenberg FST GmbH
 Technology&Innovation
 Material Compliance
 Telefon: -
 Fax: -
 Email: MaterialCompliance@fst.com

Technical data sheet in accordance with ASTM

Material

70 NBR 99006

revision index
3

revision date
5/4/2021

page 2 / 3

Tested after ASTM D 2000: M 2 BG 714 EA14 EF11 EF21 EO14 EO34 Z1 Z2 Z3

		nominal range	typical values
Hardness	Shore	70 ±5	69
Tensile strength	MPa	min. 14	15.9
Elongation at break	%	min. 250	440
A14 Change after aging in Air 70h/100°C			
Hardness	Shore A	---	2
Tensile strength	%	---	20
Elongation at break	%	---	-18
EA14 Change after aging in Distilled water 70h/100°C			
Hardness	Shore A	±10	-3
Volume	%	±15	2.4
EF11 Change after aging in Fuel A 70h/23°C			
Hardness	Shore A	±10	0
Tensile strength	%	-25	-13
Elongation at break	%	-25	-14
Volume	%	-5 to 10	1.8
EF21 Change after aging in Fuel B 70h/23°C			
Hardness	Shore A	0 to -30	-14
Tensile strength	%	-60	-50
Elongation at break	%	-60	-46
Volume	%	0 to 40	32
EO14 Change after aging in IRM 901 70h/100°C			
Hardness	Shore A	-5 to 10	4
Tensile strength	%	-25	-5
Elongation at break	%	-45	-10

Freudenberg

Freudenberg FST GmbH

Technology&Innovation

Material Compliance

Telefon: -

Fax: -

Email: MaterialCompliance@fst.com

Technical data sheet in accordance with ASTM

Material

70 NBR 99006

revision index	revision date		page	3 / 3
3	5/4/2021			
		Volume	%	-10 to 5 -6.4
E034	Change after aging in IRM 903 70h/100°C			
		Hardness	Shore A	-10 to 5 -5
		Tensile strength	%	-45 -11
		Elongation at break	%	-45 -18
		Volume	%	0 to 25 6
Z1	Compression set DIN 53517, 22 h, 100 °C		%	--- 20
Z2	Density DIN EN ISO 1183, 20 °C		g/cm ³	--- 1.27
Z3	Low Temperature DIN 3167 Teil 15 Nach DSC		°C	--- -22

The given values are based on a limited number of tests on standard test pieces (2mm sheets) produced in the laboratory. The data from finished parts can deviate from above values depending on the manufacturing process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

Freudenberg

Freudenberg FST GmbH
 Technology&Innovation
 Material Compliance

Telefon: -

Fax: -

Email: MaterialCompliance@fst.com