

Technical data sheet in accordance with ASTM

Material

70 NBR N700FWH

white

cross linking: sulfur

revision index

1

revision date

10/29/2021

page

1 / 2

Physical properties

nominal range

typical values

Density

ASTM D297, 23 °C

1.52

g/cm³

Hardness

ASTM D2240, Shore A, 23 °C

69

Shore

Modulus

100 %, ASTM D412, C, 23 °C

3.39

MPa

Modulus

200 %, ASTM D412, C, 23 °C

5.87

MPa

Modulus

300 %, ASTM D412, C, 23 °C

7.89

MPa

Tensile strength

ASTM D412, C, 23 °C

> 6

9.76

MPa

Elongation at break

ASTM D412, C, 23 °C

> 100

444

%

Temperature range

-30°C to 100°C

Declarations of conformity

No data found!

Freudenberg

Freudenberg FST GmbH

Technology&Innovation

Material Compliance

Telefon: -

Fax: -

Email: MaterialCompliance@fst.com

Technical data sheet in accordance with ASTM

Material

70 NBR N700FWH

white

cross linking: sulfur

revision index

1

revision date

10/29/2021

page 2 / 2

No ASTM D2000 properties available

The given values are based on a limited number of tests on standard test pieces (2mm sheets). The data from finished parts can deviate from above values depending on the manufacturing process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

Freudenberg

Freudenberg FST GmbH

Technology&Innovation

Material Compliance

Telefon: -

Fax: -

Email: MaterialCompliance@fst.com