

Technical data sheet in accordance with ASTM

Material

70 NBR N700R

black

cross linking: sulfur

revision index

1

revision date

9/2/2021

page

1 / 3

Physical properties

Density

ASTM D297, 23 °C

nominal range

1.26 ±0.03

typical values

1.26

g/cm³

Hardness

ASTM D2240, Shore A, 23 °C

70 ±5

68

Shore

Tensile strength

ASTM D412, C, 23 °C

> 10

16.2

MPa

Elongation at break

ASTM D412, C, 23 °C

> 250

359

%

Compression set

ASTM D395, Slab B, 22 h, 100 °C, 25 %

< 25

15

%

Declarations of conformity

No data found!

Freudenberg

Freudenberg FST GmbH

Technology&Innovation

Material Compliance

Telefon: -

Fax: -

Email: MaterialCompliance@fst.com

Technical data sheet in accordance with ASTM

Material

70 NBR N700R

black

cross linking: sulfur

revision index

1

revision date

9/2/2021

page

2 / 3

Tested after ASTM D 2000: M 2 BG 710 B14 EF11 EF21 EO14 EO34 Z1 Z2

		nominal range	typical values
Hardness	Shore	70 ±5	68
Tensile strength	MPa	min. 10	16.2
Elongation at break	%	min. 250	359
B14 Compression set 22h/100°C	%	25	15
EF11 Change after aging in Fuel A 70h/23°C			
Hardness	Shore A	±10	-1
Tensile strength	%	-25	-6
Elongation at break	%	-25	-5
Volume	%	-5 to 10	0
EF21 Change after aging in Fuel B 70h/23°C			
Hardness	Shore A	0 to -30	-18
Tensile strength	%	-60	-28
Elongation at break	%	-60	-20
Volume	%	0 to 40	24
EO14 Change after aging in IRM 901 70h/100°C			
Hardness	Shore A	-5 to 10	7
Tensile strength	%	-25	4
Elongation at break	%	-45	-15
Volume	%	-10 to 5	-7
EO34 Change after aging in IRM 903 70h/100°C			
Hardness	Shore A	-10 to 5	0
Tensile strength	%	-45	0
Elongation at break	%	-45	-12
Volume	%	0 to 25	1

Freudenberg

Freudenberg FST GmbH

Technology&Innovation

Material Compliance

Telefon: -

Fax: -

Email: MaterialCompliance@fst.com

Technical data sheet in accordance with ASTM

Material

70 NBR N700R

black

cross linking: sulfur

revision index	revision date		page	3 / 3
1	9/2/2021			
Z1	Specific Gravity ASTM D1817	g/cc	---	1.26
Z2	Change after aging in Air 70h/100°C			
	Hardness Shore A	Shore	±15	2
	Tensile strength	%	±30	0
	Elongation at break	%	-50	-18
	Volume	%	---	-2

The given values are based on a limited number of tests on standard test pieces (2mm sheets). The data from finished parts can deviate from above values depending on the manufactories process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

Freudenberg

Freudenberg FST GmbH
Technology&Innovation
Material Compliance

Telefon: -

Fax: -

Email: MaterialCompliance@fst.com