



# Material 70 NBR S1RC71NB

black

cross linking: sulfur

revision index 4	revision date 2/29/2024			page	1/2
Physical properties		nominal rang		typical values	
Hardness DIN ISO 7619-1, Shore A		70 ±	5		Shore
Tensile strength ISO 37		> 1	2		MPa
Elongation at break ISO 37		> 25	0		%
Low temperature test ISO 2921, TR10		< -2	0		°C
Compression set DIN ISO 815, Slab B, 72 h, 100	) ℃	< 4	0		%
Temperature range		-30°C to 100°C			

## **Declarations of conformity**

This overview is purely informative and does not constitute a declaration of conformity (DoC). Please refer to the actual declaration of conformity (DoC) including the conditions and its validity period.

	Country	Part	Remark	<b>Expires</b>
Info ROHS and ELV			EU 2000/53 (ELV) including EU 2011/65 and EU2015/863 (ROHS III)	see DoC

#### Freudenberg

Freudenberg Industrial Services GmbH Global Material Technology Nadja Güldner

Telefon: -Fax: -

Email: FIS.Compound.CRC@fst.com





## Material 70 NBR S1RC71NB

black

cross linking: sulfur

revision index revision date

4 2/29/2024 page 2/2

### No ASTM D2000 properties available

The given values are based on a limited number of tests on standard test pieces (2mm sheets). The data from finished parts can deviate from above values depending on the manufactories process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisons do not plan for something else.

#### Freudenberg

Freudenberg Industrial Services GmbH Global Material Technology Nadja Güldner

Telefon: -Fax: -

Email: FIS.Compound.CRC@fst.com