

# Material

## 70 VMQ P4OR71VM

auburn

cross linking: peroxidic

**revision index**

3

**revision date**

10/1/2024

**page**

1 / 2

### Physical properties

	nominal range	typical values	
<b>Hardness</b> DIN ISO 7619-1, Shore A	70 ±5	---	Shore
<b>Tensile strength</b> ISO 37	> 6	---	MPa
<b>Elongation at break</b> ISO 37	> 150	---	%
<b>Low temperature test</b> ISO 2921, TR10	< -40	---	°C
<b>Compression set</b> DIN ISO 815, Slab B, 72 h, 175 °C	< 35	---	%
<b>Temperature range</b>	-55°C to 200°C		

### Declarations of conformity

This overview is purely informative and does not constitute a declaration of conformity (DoC). Please refer to the actual declaration of conformity (DoC) including the conditions and its validity period.

	Country	Part	Remark	Expires
Info ROHS and ELV			EU 2000/53 (ELV) including EU 2011/65 and EU2015/863 (ROHS III)	see DoC
PFOA / PFOS free			see certificate	see DoC

### Freudenberg

Freudenberg Industrial Services GmbH  
 Global Material Technology  
 Nadja Güldner  
 Telefon: -  
 Fax: -  
 Email: FIS.Compound.CRC@fst.com

## **Material**

### **70 VMQ P4OR71VM**

auburn

cross linking: peroxidic

**revision index**

3

**revision date**

10/1/2024

**page** 2 / 2

### **No ASTM D2000 properties available**

The nominal ranges listed in this document are based on the ISO 3601-5 Standard (Fluid power systems - O-rings - Specification of elastomeric materials for industrial applications). The given values are based on a limited number of tests on standard test pieces (2mm sheets). The data from finished parts can deviate from above values depending on the manufactories process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisons do not plan for something else.

### **Freudenberg**

Freudenberg Industrial Services GmbH  
Global Material Technology  
Nadja Güldner  
Telefon: -  
Fax: -  
Email: FIS.Compound.CRC@fst.com