

# Material

## 71 ACM 112144

black

**revision index**  
1

**revision date**  
9/24/2009

**page** 1 / 3

### Physical properties

	nominal range	typical values	
<b>Density</b> DIN EN ISO 1183-1, 23 °C	---	1.36	g/cm <sup>3</sup>
<b>Hardness</b> DIN ISO 7619-1, Shore A, 23 °C	---	68	Shore
<b>Modulus</b> 100 %, DIN 53504, S2, 23 °C	---	9.4	MPa
<b>Tensile strength</b> DIN 53504, S2, 23 °C	---	11.4	MPa
<b>Elongation at break</b> DIN 53504, S2, 23 °C	---	188	%

### Declarations of conformity

This overview is purely informative and does not constitute a declaration of conformity (DoC). Please refer to the actual declaration of conformity (DoC) including the conditions and its validity period.

	Country	Part	Remark	Expires
Info ROHS and ELV			EU 2000/53 (ELV) including EU 2011/65 and EU2015/863 (ROHS III)	see DoC

### Freudenberg

Freudenberg FST GmbH  
Technology&Innovation  
Material Compliance

Telefon: -

Fax: -

Email: MaterialCompliance@fst.com

# Material

## 71 ACM 112144

black

revision index

1

revision date

9/24/2009

page

2 / 3

Tested after ASTM D 2000: M 5 DH 706 A26 B16 EO16 EO36 F13

		nominal range	typical values
Hardness	Shore	70 ±5	69
Tensile strength	MPa	min. 6	8.9
Elongation at break	%	min. 100	180
<b>A26 Change after aging in Air 70h/150°C</b>			
Hardness	Shore	10	6
Tensile strength	%	-25	20
Elongation at break	%	-30	-27
<b>B16 Compression set 22h/150°C</b>			
	%	60	54
<b>EO16 Change after aging in IRM 901 70h/150°C</b>			
Hardness	Shore	-5 to 10	3
Tensile strength	%	-20	18
Elongation at break	%	-40	-5
Volume	%	±5	-2
<b>EO36 Change after aging in IRM 903 70h/150°C</b>			
Hardness	Shore	-15	-5
Tensile strength	%	-40	5
Elongation at break	%	-40	16
Volume	%	25	11
<b>F13 Low-temperature resistance after 3 min at -10 °C 3min./-10°C</b>			
		pass	pass

The given values are based on a limited number of tests on standard test pieces (2mm sheets) produced in the laboratory. The data from finished parts can deviate from above values depending on the manufactories process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions,

### Freudenberg

Freudenberg FST GmbH

Technology&Innovation

Material Compliance

Telefon: -

Fax: -

Email: MaterialCompliance@fst.com

**Material**  
**71 ACM 112144**

black

**revision index**

1

**revision date**

9/24/2009

**page** 3 / 3

inasmuch as statutory provisions do not plan for something else.

**Freudenberg**

Freudenberg FST GmbH  
Technology&Innovation  
Material Compliance

Telefon: -

Fax: -

Email: [MaterialCompliance@fst.com](mailto:MaterialCompliance@fst.com)