

Material

72 NBR 902

blue

cross linking: sulfur

revision index

10

revision date

9/26/2024

page

1 / 3

Physical properties

	nominal range	typical values	
Density DIN EN ISO 1183-1	1.43 ±0.02	1.43	g/cm³
Hardness DIN ISO 7619-1	75 ±5	75	Shore
Rebound resilience DIN 53512	---	26	%
Modulus 100 %, DIN 53504, S2	> 4	7.2	MPa
Tensile strength DIN 53504, S2	> 10	13.8	MPa
Elongation at break DIN 53504, S2	> 300	360	%
Compression set DIN ISO 815, 22 h, 100 °C	< 40	30	%
Low Temperature ISO 11357-2, DSC	---	-29	°C
Temperature range	-40°C to 100°C		

Declarations of conformity

This overview is purely informative and does not constitute a declaration of conformity (DoC). Please refer to the actual declaration of conformity (DoC) including the conditions and its validity period.

	Country	Part	Remark	Expires
ADI Free			see certificate	see DoC
Info ROHS and ELV			EU 2000/53 (ELV) including EU 2011/65 and EU2015/863 (ROHS III)	see DoC

Freudenberg

Freudenberg FST GmbH
Technology&Innovation
Material Compliance

Telefon: -
Fax: -
Email: MaterialCompliance@fst.com



Material

72 NBR 902

blue

cross linking: sulfur

revision index

10

revision date

9/26/2024

page

2 / 3

Tested after ASTM D 2000: M 2 BG 710 EA14 EF11 EF21 EO14 EO34 Z1 Z2

		nominal range	typical values
Tensile strength	MPa	min. 10	13.8
Elongation at break	%	min. 250	360
EA14 Change after aging in Distilled water 70h/100°C			
Hardness	Shore A	±10	3
Volume	%	±15	5
EF11 Change after aging in Fuel A 70h/23°C			
Hardness	Shore A	±10	-1
Tensile strength	%	-25	-5
Elongation at break	%	-25	-10
Volume	%	-5 to 10	2
EF21 Change after aging in Fuel B 70h/23°C			
Hardness	Shore A	0 to -30	-12
Tensile strength	%	-60	-28
Elongation at break	%	-60	-43
Volume	%	0 to 40	28
EO14 Change after aging in IRM 901 70h/100°C			
Hardness	Shore A	-5 to 10	5
Tensile strength	%	-25	9
Elongation at break	%	-45	-20
Volume	%	-10 to 5	-5
EO34 Change after aging in IRM 903 70h/100°C			
Hardness	Shore A	-10 to 5	-3
Tensile strength	%	-45	-8
Elongation at break	%	-45	-18

Freudenberg

Freudenberg FST GmbH
Technology&Innovation
Material Compliance

Telefon: -

Fax: -

Email: MaterialCompliance@fst.com



Material

72 NBR 902

blue

cross linking: sulfur

revision index	revision date		page	3 / 3
10	9/26/2024			
	Volume	%	0 to 25	8
Z1	Low Temperature DIN 3761 Teil15	°C	---	-29
Z2	Hardness Shore A, 23 °C	Shore	75 ±5	72

Preferred area of applications: Radial Shaft Seals.

Very good resistance in motor oil based on mineral oil

Attention!

In synthetic oils (polyalkylene-glycols / polyalphaolefins) please consider that the max. working temperature mustn't exceed 80 °C

The given values are based on a limited number of tests on standard test pieces (2mm sheets) produced in the laboratory. The data from finished parts can deviate from above values depending on the manufactories process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

Freudenberg

Freudenberg FST GmbH
Technology&Innovation
Material Compliance

Telefon: -
Fax: -
Email: MaterialCompliance@fst.com

