

Material

75 FKM 38269

PHASED OUT
Revision Index
 01

Revision Date
 06.03.2015
General Data
 Colour: black
 Type of cross-linking: Peroxidic

Declaration of Compliance for - Food & Beverage - Pharmaceutical is available upon request for selected articles. Please contact your known sales contact or send an email to info@fst.com.

Physical Properties

	Nominal Range	Typical Value
Density ASTM D1817, 23 °C	2.11 ±0.03	g/cm ³
Hardness DIN ISO 7619-1, Shore A, 23 °C	75 ±5	Shore
Tensile strength DIN 53504, S2, 23 °C		23.7 MPa
Elongation at break DIN 53504, S2, 23 °C		240 %
Compression set ASTM D395, B, 24 h, 200 °C, 25 %		19 %
Low temperature ASTM D1329, TR10		-15 °C

Temperature Range

static: -25 to 200 °C

The given values are based on a limited number of tests on standard test pieces (2mm sheets) produced in the laboratory. The data from finished parts can deviate from above values depending on the manufactories process and the component geometry. The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

Print date: 29.04.2025