

Material 75 FKM V75

Revision Index
12

Revision Date
13.11.2023

General Data

Colour: black
Type of cross-linking: Bisphenol cure system

Physical Properties	Nominal Range	Typical Value	
Density DIN EN ISO 1183-1, 23 °C	1.85 ±0.03	1.85	g/cm ³
Hardness DIN ISO 7619-1, Shore A, 23 °C		77	Shore
Modulus 100 %, DIN 53504, S2, 23 °C		9.2	MPa
Tensile strength DIN 53504, S2, 23 °C		15.6	MPa
Elongation at break DIN 53504, S2, 23 °C		156	%
Compression set DIN ISO 815, B, 24 h, 200 °C, 25 %		12	%
Density ASTM D297	1.85 ±0.02	1.85	g/cm ³
Hardness ASTM D2240, Shore A	76 ±3	77	Shore
Modulus 100 %, ASTM D412, C	>6	9	MPa
Modulus 100 %, ASTM D412, C	>870	1305	psi
Tensile strength ASTM D412, C	>13	15	MPa
Tensile strength ASTM D412, C	>1885	2176	psi
Elongation at break ASTM D412, C	>150	173	%
Compression set ASTM D395, B, 22 h, 175 °C, 25 %		8	%
Compression set ASTM D395, B, 22 h, 200 °C, 25 %		12	%
Low temperature ASTM D1329, TR10		-15	°C
Low temperature test ASTM D1329, TR10		5	°F
Density ASTM D297, 23 °C	1.86 ±0.02	1.86	g/cm ³
Hardness ASTM D2240, Shore A	75 ±5	79	Shore
Tensile strength ASTM D1414		2140	psi

Material

75 FKM V75

	Revision Index	Revision Date
	12	13.11.2023
Elongation at break ASTM D1414	178	%
Low temperature test ASTM D1329, TR10	1	°F
Compression set ASTM D395, 22 h, 200 °C, 25 %	11	%
Low temperature ASTM D1329, TR10	-16.4	°C
Compression set ASTM D395, 336 h, 200 °C, 25 %	40	%

The given values are based on a limited number of tests on standard test pieces (2mm sheets) produced in the laboratory. The data from finished parts can deviate from above values depending on the manufacturing process and the component geometry. The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

Print date: 29.04.2025