

Material

75 FFKM Z7257

black

cross linking: peroxidic

FFKM

revision index

2

revision date

9/26/2019

page

1 / 2

Physical properties

	nominal range	typical values	
Density DIN EN ISO 1183, 23 °C	2.00 - 2.06	2.02	g/cm ³
Hardness DIN ISO 7619-1, Shore A, 23 °C	76 - 82	78	Shore
Tensile strength DIN 53504, S2, 23 °C	> 14	17.6	MPa
Elongation at break DIN 53504, S2, 23 °C	> 120	150	%
Compression set ASTM D395, Slab B, 70 h, 275 °C, 25 %	< 30	28	%

Declarations of conformity

No data found!

Freudenberg

Freudenberg FST GmbH

Technology&Innovation

Material Compliance

Telefon: -

Fax: -

Email: MaterialCompliance@fst.com

Material

75 FFKM Z7257

black

cross linking: peroxidic

FFKM

revision index

2

revision date

9/26/2019

page

2 / 2

No ASTM D2000 properties available

AMS-7257 requirements

The given values are based on a limited number of tests on standard test pieces (2mm sheets) produced in the laboratory. The data from finished parts can deviate from above values depending on the manufactories process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

Freudenberg

Freudenberg FST GmbH

Technology&Innovation

Material Compliance

Telefon: -

Fax: -

Email: MaterialCompliance@fst.com