

Material

75 FKM 239961

black

cross linking: peroxidic

revision index

5

revision date

3/7/2023

page

1 / 3

Physical properties

	nominal range	typical values	
Density DIN EN ISO 1183, 23 °C	1.89 ±0.03	1.89	g/cm ³
Hardness DIN ISO 7619-1, Shore A, 23 °C	72 ±5	72	Shore
Modulus 100 %, DIN 53504, S2, 23 °C	> 2.5	3.5	MPa
Tensile strength DIN 53504, S2, 23 °C	> 14.5	16.7	MPa
Elongation at break DIN 53504, S2, 23 °C	> 300	420	%
Compression set DIN ISO 815, Slab B, 24 h, 175 °C, 25 %	< 30	20	%
Low Temperature ISO 11357-2, DSC	---	-19	°C
Temperature range	-25°C to 200°C		

Declarations of conformity

This overview is purely informative and does not constitute a declaration of conformity (DoC). Please refer to the actual declaration of conformity (DoC) including the conditions and its validity period.

	Country	Part	Remark	Expires
(EG) 1935/2004	EU		food	see DoC
(EG) 2023/2006 (GMP)	EU		(EG) 2023/2006 (GMP)	see DoC
3-A Sanitary	USA	Seals	Class I	12 / 2027
BFR XXI, Kat 4	DE		food	see DoC
BPA/Phthalate free			BPA/Phthalate free	see DoC
BSE/TSE-free	-	Seals		11 / 2028
Cytotoxicity USP chapter 87 & 88 (class VI)	-	Seals		09 / 2032
FDA	USA	Seals	§ 177.2600	see DoC
Info ROHS and ELV			EU 2000/53 (ELV) including EU 2011/65 and EU2015/863 (ROHS III)	see DoC

Freudenberg

Freudenberg FST GmbH
Technology&Innovation
Material Compliance

Telefon: -

Fax: -

Email: MaterialCompliance@fst.com

Material
75 FKM 239961

black

cross linking: peroxidic

revision index

5

revision date

3/7/2023

page 2 / 3

Freudenberg

Freudenberg FST GmbH
Technology&Innovation
Material Compliance

Telefon: -

Fax: -

Email: MaterialCompliance@fst.com

Material

75 FKM 239961

black

cross linking: peroxidic

revision index

5

revision date

3/7/2023

page 3 / 3

No ASTM D2000 properties available

The given values are based on a limited number of tests on standard test pieces (2mm sheets). The data from finished parts can deviate from above values depending on the manufacturing process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

Freudenberg

Freudenberg FST GmbH

Technology&Innovation

Material Compliance

Telefon: -

Fax: -

Email: MaterialCompliance@fst.com