

Technical data sheet in accordance with AMS 7287

Material

75 FKM V199

black

cross linking: peroxidic

revision index

2

revision date

12/4/2018

page

1 / 2

Physical properties

	nominal range	typical values	
Density ASTM D297	1.73 ±0.02	1.73	g/cm ³
Hardness ASTM D2240, Shore A	75 ±5	76	Shore
Hardness ASTM D2240, Shore M	---	80	Shore
Tensile strength ASTM D1414	≥ 1600	1804	Psi
Elongation at break ASTM D1414	≥ 120	186	%
Low temperature test ASTM D1329, TR10	-29	-31	°C
Glass Transition Temperature ASTM D7426	-29	-30	°C
Compression set ASTM D395, 22 h, 200 °C, 25 %	≤ 20	7	%
Compression set ASTM D395, 336 h, 200 °C, 25 %	≤ 50	26	%

Declarations of conformity

No data found!

Freudenberg

Freudenberg FST GmbH

Technology&Innovation

Material Compliance

Telefon: -

Fax: -

Email: MaterialCompliance@fst.com

Technical data sheet in accordance with AMS 7287

Material

75 FKM V199

black

cross linking: peroxidic

revision index

2

revision date

12/4/2018

page 2 / 2

No ASTM D2000 properties available

The given values are based on a limited number of tests on standard test pieces (2mm sheets). The data from finished parts can deviate from above values depending on the manufacturing process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

Freudenberg

Freudenberg FST GmbH
Technology&Innovation
Material Compliance

Telefon: -

Fax: -

Email: MaterialCompliance@fst.com