

Technical data sheet in accordance with AMS 7276

Material

75 FKM V75

black

cross linking: bisphenolically

revision index
12

revision date
11/13/2023

page 1 / 2

Physical properties

	nominal range	typical values	
Density ASTM D297, 23 °C	1.86 ±0.02	1.86	g/cm ³
Hardness ASTM D2240, Shore A	75 ±5	79	Shore
Tensile strength ASTM D1414	>= 1400	2140	Psi
Elongation at break ASTM D1414	>= 125	178	%
Low temperature test ASTM D1329, TR10	<= 5	1	°F
Compression set ASTM D395, 22 h, 200 °C, 25 %	<= 15	11	%
Compression set ASTM D395, 336 h, 200 °C, 25 %	<= 40	40	%

Declarations of conformity

This overview is purely informative and does not constitute a declaration of conformity (DoC). Please refer to the actual declaration of conformity (DoC) including the conditions and its validity period.

Country	Part	Remark	Expires
ADI Free		see certificate	see DoC
AMS 7276			see DoC
Info ROHS and ELV		EU 2000/53 (ELV) including EU 2011/65 and EU2015/863 (ROHS III)	see DoC

Freudenberg

Freudenberg FST GmbH
Technology&Innovation
Material Compliance

Telefon: -
Fax: -
Email: MaterialCompliance@fst.com



Technical data sheet in accordance with AMS 7276

Material 75 FKM V75

black

cross linking: bisphenolically

revision index

12

revision date

11/13/2023

page

2 / 2

No ASTM D2000 properties available

The given values are based on a limited number of tests on standard test pieces (2mm sheets) produced in the laboratory. The data from finished parts can deviate from above values depending on the manufacturing process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

Freudenberg

Freudenberg FST GmbH
Technology&Innovation
Material Compliance

Telefon: -
Fax: -
Email: MaterialCompliance@fst.com

