

Technical data sheet in accordance with ASTM

# Material

## 75 FKM V7513Z

black

cross linking: bisphenolically

**revision index**

1

**revision date**

10/1/2021

**page**

1 / 3

### Physical properties

	nominal range	typical values	
<b>Density</b> ASTM D 297	---	1.85	g/cm <sup>3</sup>
<b>Hardness</b> ASTM D 2240, Shore A	75 ±5	74	Shore
<b>Tensile strength</b> ASTM D 412	> 10	16.41	MPa
<b>Elongation at break</b> ASTM D 412	> 175	230	%
<b>Tear strength</b> ASTM D624, C	---	30.4	KN/m
<b>Modulus</b> 100 %, ASTM D412	---	6.13	MPa
<b>Modulus</b> 200 %, ASTM D412	---	14.15	MPa
<b>Compression set</b> ASTM D 395, Slab B, 22 h, 175 °C	---	8	%
<b>Compression set</b> ASTM D 395, Slab B, 22 h, 200 °C	< 50	12	%

### Declarations of conformity

No data found!

### Freudenberg

Freudenberg FST GmbH

Technology&Innovation

Material Compliance

Telefon: -

Fax: -

Email: MaterialCompliance@fst.com

Technical data sheet in accordance with ASTM

# Material

## 75 FKM V7513Z

black

cross linking: bisphenolically

**revision index**

1

**revision date**

10/1/2021

**page**

2 / 3

**Tested after ASTM D 2000: M 4 HK 710 A1-11 B38 EF31 EO78 Z1 Z2 Z3 Z4 Z5 Z6**

		<b>nominal range</b>	<b>typical values</b>
Tensile strength	MPa	min. 10	16.4
Elongation at break	%	min. 175	230
<b>A1-11 Change after aging in Air 70h/275°C</b>			
Hardness	Shore A	10	-1
Tensile strength	%	-40	-29
Elongation at break	%	-20	35
<b>B37 Compression set 22h/175°C</b>	%	---	8
<b>B38 Compression set 22h/200°C</b>	%	50	12
<b>EF31 Change after aging in Fuel C 70h/23°C</b>			
Hardness	Shore	±5	-3
Tensile strength	MPa	-25	-16
Elongation at break	%	-20	-4
Volume	%	0 to 10	3.7
<b>EO78 Change after aging in Fluid No. 101 70h/200°C</b>			
Hardness	Shore	-15 to 5	-7
Tensile strength	MPa	-40	-7
Elongation at break	%	-20	10
Volume	%	0 to 15	10.9
<b>Z1 Modulus 100 %, ASTM D412</b>	MPa	---	6.13
<b>Z2 Modulus 200 %, ASTM D412</b>	MPa	---	14.15
<b>Z3 Density</b>	g/cm <sup>3</sup>	---	1.847

### Freudenberg

Freudenberg FST GmbH

Technology&Innovation

Material Compliance

Telefon: -

Fax: -

Email: MaterialCompliance@fst.com

Technical data sheet in accordance with ASTM

# Material

## 75 FKM V7513Z

black

cross linking: bisphenolically

revision index	revision date		page	3 / 3
1	10/1/2021			
<b>Z4</b>	<b>Tear strength ASTM D624, C</b>	KN/m	---	30.4
<b>Z5</b>	<b>Change after aging in Air 70h/250°C</b>			
	Hardness ASTM D 2240, Shore A	Shore	---	2
	Tensile strength ASTM D 412	%	---	-1
	Elongation at break ASTM D 412	%	---	1
	volume change	%	---	-1
<b>Z6</b>	<b>Hardness ASTM D2240, Shore A</b>	Shore	75 ±5	74

The given values are based on a limited number of tests on standard test pieces (2mm sheets). The data from finished parts can deviate from above values depending on the manufacturing process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

### Freudenberg

Freudenberg FST GmbH  
Technology&Innovation  
Material Compliance

Telefon: -

Fax: -

Email: MaterialCompliance@fst.com