

Technical data sheet in accordance with ASTM

Material

75 FKM V751Z

black

cross linking: bisphenolically

revision index

2

revision date

2/25/2022

page

1 / 3

Physical properties

	nominal range	typical values	
Density ASTM D297-19	1.87 ±0.05	1.87	g/cm ³
Hardness ASTM D2240-15, Shore A	75 ±5	73	Shore
Tensile strength ASTM D412-	---	11.6	MPa
Elongation at break ASTM D412-16	---	235	%
Compression set ASTM D395-18, 22 h, 200 °C	---	12	%

Declarations of conformity

No data found!

Freudenberg

Freudenberg FST GmbH

Technology&Innovation

Material Compliance

Telefon: -

Fax: -

Email: MaterialCompliance@fst.com

Technical data sheet in accordance with ASTM

Material

75 FKM V751Z

black

cross linking: bisphenolically

revision index

2

revision date

2/25/2022

page

2 / 3

Tested after ASTM D 2000: M 2 HK 710 A1-10 B38 EF31 EO78 Z1 Z2

		nominal range	typical values
Tensile strength	MPa	min. 10	11.6
Elongation at break	%	min. 175	235
A1-10 Change after aging in Air 70h/250°C			
Hardness	Shore A	10	1
Tensile strength	%	-25	2
Elongation at break	%	-25	-5
B38 Compression set 22h/200°C	%	50	12
EF31 Change after aging in Fuel C 70h/23°C			
Hardness	Shore	±5	-3
Tensile strength	%	-25	-12
Elongation at break	%	-20	-7
Volume	%	0 to 10	4
EO78 Change after aging in Fluid No. 101 70h/200°C			
Hardness	Shore	-15 to 5	-6
Tensile strength	%	-40	-15
Elongation at break	%	-20	-6
Volume	%	0 to 15	11
Z1 Hardness ASTM D2240, Shore A, 23 °C	Shore	75 ±5	73
Z2 Density ASTM D297, 23 °C	g/cm ³	---	1.87

The given values are based on a limited number of tests on standard test pieces (2mm sheets). The data from finished parts can deviate from above values depending on the manufacturing process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions,

Freudenberg

Freudenberg FST GmbH

Technology&Innovation

Material Compliance

Telefon: -

Fax: -

Email: MaterialCompliance@fst.com

Technical data sheet in accordance with ASTM

Material
75 FKM V751Z

black

cross linking: bisphenolically

revision index

2

revision date

2/25/2022

page 3 / 3

inasmuch as statutory provisions do not plan for something else.

Freudenberg

Freudenberg FST GmbH
Technology&Innovation
Material Compliance

Telefon: -

Fax: -

Email: MaterialCompliance@fst.com