

Technical data sheet in accordance with ASTM

# Material

## 75 FKM V75BR

brown

cross linking: bisphenolically

**revision index**

5

**revision date**

10/28/2020

**page**

1 / 2

### Physical properties

	nominal range	typical values	
<b>Density</b> ASTM D297, 23 °C	---	2.00	g/cm <sup>3</sup>
<b>Hardness</b> ASTM D2240, Shore A, 23 °C	75 ±5	76	Shore
<b>Tensile strength</b> ASTM D412, C, 23 °C	> 10	13.1	MPa
<b>Elongation at break</b> ASTM D412, C, 23 °C	> 175	190	%
<b>Compression set</b> ASTM D395, Slab B, 22 h, 200 °C, 25 %	< 50	15	%

### Declarations of conformity

This overview is purely informative and does not constitute a declaration of conformity (DoC). Please refer to the actual declaration of conformity (DoC) including the conditions and its validity period.

	Country	Part	Remark	Expires
ADI Free				see DoC

### Freudenberg

Freudenberg FST GmbH  
Technology&Innovation  
Material Compliance

Telefon: -  
Fax: -  
Email: [MaterialCompliance@fst.com](mailto:MaterialCompliance@fst.com)



Technical data sheet in accordance with ASTM

## Material

### 75 FKM V75BR

brown

cross linking: bisphenolically

**revision index**

5

**revision date**

10/28/2020

**page** 2 / 2

#### No ASTM D2000 properties available

The given values are based on a limited number of tests on standard test pieces (2mm sheets) produced in the laboratory. The data from finished parts can deviate from above values depending on the manufactories process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

#### Freudenberg

Freudenberg FST GmbH  
Technology&Innovation  
Material Compliance

Telefon: -  
Fax: -  
Email: [MaterialCompliance@fst.com](mailto:MaterialCompliance@fst.com)

