

Technical data sheet in accordance with MIL -DTL-25988C Class

Material

75 FVMQ F75

blue

FVMQ

revision index

1

revision date

2/15/2018

page

1 / 3

Physical properties

	nominal range	typical values	
Density ASTM D792, hydrostatic method	1.53 ±0.03	1.53	g/cm ³
Hardness ASTM D2240, Shore A, plied disk	75 ±5	73	Shore
Tensile strength ASTM D1414	> 5.5	5.8	MPa
Tensile strength ASTM D1414	> 800	842	Psi
Elongation at break ASTM D1414	> 90	213	%
Compression set ASTM D395, 24 h, 70 °C, 25 %	< 20	11	%
Compression set ASTM D395, 22 h, 175 °C, 25 %	< 35	14	%
Low temperature test ASTM D1329, TR10	< -57	-63	°C
Low temperature test ASTM D1329, TR10	< -70	-81	°F

Declarations of conformity

No data found!

Change after aging

in Air: 70h/250°C

		nominal range		Typ. values	
		Nominal	Base value	After aging	difference
Hardness (ASTM D2240, Shore A, plied disk)	Shore	---	73	74	1
Tensile strength (ASTM D1414)	%	---			
Elongation at break (ASTM D1414)	%	---	213	188	-12 %
weight change	%	---		-0.5	

Freudenberg

Freudenberg FST GmbH

Technology&Innovation

Material Compliance

Telefon: -

Fax: -

Email: MaterialCompliance@fst.com

Technical data sheet in accordance with MIL -DTL-25988C Class

Material

75 FVMQ F75

blue

FVMQ

revision index

1

revision date

2/15/2018

page 2 / 3

Change after aging in AMS 2629 Type 1: 22h/23°C

Hardness (ASTM D2240, Shore A, plied disk)
Tensile strength (ASTM D1414)
Elongation at break (ASTM D1414)
volume change (ASTM D471)

Shore
%
%
%

nominal range		Typ. values		
Nominal	Base value	After aging	difference	
---	73	69	-4	
---	213	202	-5 %	
---		18.1		

Change after aging in AMS 3021: 70h/175°C

Hardness (ASTM D2240, Shore A, plied disk)
Tensile strength (ASTM D1414)
Elongation at break (ASTM D1414)
volume change (ASTM D471)
Compression set (ASTM D395, Slab B, 70 h, 175 °C, 25 %, CS> 0.110 inch)

Shore
%
%
%
%

nominal range		Typ. values		
Nominal	Base value	After aging	difference	
---	73	66	-7	
---	213	227	7 %	
---		10.8		

Freudenberg

Freudenberg FST GmbH
Technology&Innovation
Material Compliance

Telefon: -

Fax: -

Email: MaterialCompliance@fst.com

Technical data sheet in accordance with MIL -DTL-25988C Class

Material

75 FVMQ F75

blue

FVMQ

revision index	revision date	page
1	2/15/2018	3 / 3

No ASTM D2000 properties available

The given values are based on a limited number of tests on standard test pieces (2mm sheets) produced in the laboratory. The data from finished parts can deviate from above values depending on the manufactories process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

Freudenberg

Freudenberg FST GmbH

Technology&Innovation

Material Compliance

Telefon: -

Fax: -

Email: MaterialCompliance@fst.com