

# Material 75 NBR 115718

**revision index**  
1

**revision date**  
5/7/2018

**page** 1 / 2

**Physical properties**

	<b>nominal range</b>	<b>typical values</b>	
<b>Density</b> DIN EN ISO 1183-1	1.24 ±0.02	1.25	g/cm <sup>3</sup>
<b>Hardness</b> DIN ISO 7619-1	75 ±5	75	Shore
<b>Modulus</b> 100 %, DIN 53504, S2	> 5	6.1	MPa
<b>Tensile strength</b> DIN 53504, S2	> 11	12.1	MPa
<b>Elongation at break</b> DIN 53504, S2	> 150	255	%

**Declarations of conformity**  
**No data found!**

**Freudenberg**

Freudenberg FST GmbH  
Technology&Innovation  
Material Compliance  
Telefon: -  
Fax: -  
Email: MaterialCompliance@fst.com

## Material

### 75 NBR 115718

**revision index**

1

**revision date**

5/7/2018

**page**

2 / 2

#### **No ASTM D2000 properties available**

The given values are based on a limited number of tests on standard test pieces (2mm sheets) produced in the laboratory. The data from finished parts can deviate from above values depending on the manufacturing process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

#### **Freudenberg**

Freudenberg FST GmbH

Technology&amp;Innovation

Material Compliance

Telefon: -

Fax: -

Email: [MaterialCompliance@fst.com](mailto:MaterialCompliance@fst.com)