

Technical data sheet in accordance with AMS -P- 83461

# Material

## 75 NBR N456

black

**revision index**

3

**revision date**

2/15/2018

**page**

1 / 3

### Physical properties

	nominal range	typical values	
<b>Density</b> ASTM D297	---	1.17	g/cm <sup>3</sup>
<b>Hardness</b> ASTM D2240, Shore A	---	70	Shore
<b>Hardness</b> ASTM D2240, Shore M	---	77	Shore
<b>Tensile strength</b> ASTM D1414	---	1796	Psi
<b>Elongation at break</b> ASTM D1414	---	159	%
<b>Modulus</b> 100 %, ASTM D1414	---	780	Psi
<b>Low temperature test</b> ASTM D1329, TR10	---	-62	°F
<b>Compression set</b> ASTM D395, 70 h, 135 °C, 25 %	---	64	%
<b>Compression set</b> ASTM D395, 1440 h, 23 °C, 25 %	---	11	%

### Declarations of conformity

No data found!

### Freudenberg

Freudenberg FST GmbH

Technology&Innovation

Material Compliance

Telefon: -

Fax: -

Email: MaterialCompliance@fst.com

Technical data sheet in accordance with AMS -P- 83461

# Material

## 75 NBR N456

black

### revision index

3

### revision date

2/15/2018

page 2 / 3

### Change after aging in ARM 201: 70h/135°C

Hardness (ASTM D2240, Shore A)  
Tensile strength (ASTM D1414)  
Elongation at break (ASTM D1414)  
volume change (ASTM D471)  
Compression set (ASTM D395, Slab B, 70 h, 135 °C, 25 %)  
Compression set (ASTM D395, Slab B, 1440 h, 23 °C, 25 %)  
Low temperature test (ASTM D1329, TR10)

Shore  
%  
%  
%  
%  
%  
°F

### nominal range

Nominal Base value After aging difference

--- 70 67 -3  
--- 159 111 -30 %  
--- 20  
---  
---

### Change after aging in MIL-H-83282: 70h/135°C

Hardness (ASTM D2240, Shore A)  
Tensile strength (ASTM D1414)  
Elongation at break (ASTM D1414)  
volume change (ASTM D471)  
Compression set (ASTM D395, Slab B, 70 h, 135 °C, 25 %)  
Low temperature test (ASTM D1329, TR10)

Shore  
%  
%  
%  
%  
°F

### nominal range

Nominal Base value After aging difference

--- 70 69 -1  
--- 159 117 -26 %  
--- 6  
---  
---

## Freudenberg

Freudenberg FST GmbH

Technology&Innovation

Material Compliance

Telefon: -

Fax: -

Email: MaterialCompliance@fst.com

Technical data sheet in accordance with AMS -P- 83461

## **Material**

### **75 NBR N456**

black

**revision index**

3

**revision date**

2/15/2018

**page**

3 / 3

**No ASTM D2000 properties available**

#### **AMS-P-83461**

The given values are based on a limited number of tests on standard test pieces (2mm sheets) produced in the laboratory. The data from finished parts can deviate from above values depending on the manufactories process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

#### **Freudenberg**

Freudenberg FST GmbH

Technology&Innovation

Material Compliance

Telefon: -

Fax: -

Email: [MaterialCompliance@fst.com](mailto:MaterialCompliance@fst.com)