

# Material

## 75 Simriz 484

black

cross linking: peroxidic  
**FFKM**

**revision index**  
9

**revision date**  
9/16/2009

**page** 1 / 2

### Physical properties

	nominal range	typical values	
<b>Density</b> DIN EN ISO 1183-1, 23 °C	2.02 ±0.03	2.02	g/cm <sup>3</sup>
<b>Hardness</b> DIN ISO 7619-1, Shore A, 23 °C	75 ±5	75	Shore
<b>Modulus</b> 100 %, DIN 53504, S2, 23 °C	---	8.6	MPa
<b>Tensile strength</b> DIN 53504, S2, 23 °C	> 16	22.1	MPa
<b>Elongation at break</b> DIN 53504, S2, 23 °C	> 130	165	%
<b>Compression set</b> DIN ISO 815, Slab I, 70 h, 200 °C, 25 %	< 45	33	%
<b>Low Temperature</b> DIN 53765, DSC	---	-7	°C
<b>Temperature range</b>	-10°C to 230°C      short term: 260°C		

### Declarations of conformity

This overview is purely informative and does not constitute a declaration of conformity (DoC). Please refer to the actual declaration of conformity (DoC) including the conditions and its validity period.

	Country	Part	Remark	Expires
3-A Sanitary	USA	Seals	Class I	12 / 2027
ADI Free			see certificate	see DoC
BPA/Phthalate free			BPA/Phthalate free	see DoC
Cytotoxicity USP chapter 87 & 88 (class VI)	USA	Seals		03 / 2033
FDA	USA	Seals		07 / 2026
Info ROHS and ELV			EU 2000/53 (ELV) including EU 2011/65 and EU2015/863 (ROHS III)	see DoC
PFOA / PFOS free			see certificate	see DoC

### Freudenberg

Freudenberg FST GmbH  
Technology&Innovation  
Material Compliance

Telefon: -  
Fax: -  
Email: MaterialCompliance@fst.com



## Material

### 75 Simriz 484

black

cross linking: peroxidic  
**FFKM**

**revision index**  
9

**revision date**  
9/16/2009

**page** 2 / 2

**No ASTM D2000 properties available**

The given values are based on a limited number of tests on standard test pieces (2mm sheets) produced in the laboratory. The data from finished parts can deviate from above values depending on the manufactories process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisons do not plan for something else.

### Freudenberg

Freudenberg FST GmbH  
Technology&Innovation  
Material Compliance

Telefon: -  
Fax: -  
Email: [MaterialCompliance@fst.com](mailto:MaterialCompliance@fst.com)

