

Material

75 Simriz 484

black

cross linking: peroxidic
FFKM

revision index
9

revision date
9/16/2009

page 1 / 2

Physical properties

	nominal range	typical values	
Density DIN EN ISO 1183-1, 23 °C	2.02 ±0.03	2.02	g/cm ³
Hardness DIN ISO 7619-1, Shore A, 23 °C	75 ±5	75	Shore
Modulus 100 %, DIN 53504, S2, 23 °C	---	8.6	MPa
Tensile strength DIN 53504, S2, 23 °C	> 16	22.1	MPa
Elongation at break DIN 53504, S2, 23 °C	> 130	165	%
Compression set DIN ISO 815, Slab I, 70 h, 200 °C, 25 %	< 45	33	%
Low Temperature DIN 53765, DSC	---	-7	°C
Temperature range	-10°C to 230°C short term: 260°C		

Declarations of conformity

This overview is purely informative and does not constitute a declaration of conformity (DoC). Please refer to the actual declaration of conformity (DoC) including the conditions and its validity period.

	Country	Part	Remark	Expires
3-A Sanitary ADI Free Cytotoxicity USP chapter 87 & 88 (class VI)	USA	Seals	Class I see certificate	12 / 2027 see DoC 03 / 2033
FDA Info ROHS and ELV	USA	Seals		07 / 2026 see DoC
PFOA / PFOS free USP Class VI Ch. 88 - 121 °C	USA	Seals	EU 2000/53 (ELV) including EU 2011/65 and EU2015/863 (ROHS III) see certificate 121 °C	see DoC see DoC

Freudenberg

Freudenberg FST GmbH
Technology&Innovation
Material Compliance

Telefon: -
Fax: -
Email: MaterialCompliance@fst.com



Material 75 Simriz 484

black

cross linking: peroxidic
FFKM

revision index
9

revision date
9/16/2009

page 2 / 2

No ASTM D2000 properties available

The given values are based on a limited number of tests on standard test pieces (2mm sheets) produced in the laboratory. The data from finished parts can deviate from above values depending on the manufactories process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisons do not plan for something else.

Freudenberg

Freudenberg FST GmbH
Technology&Innovation
Material Compliance

Telefon: -
Fax: -
Email: MaterialCompliance@fst.com

