

Material

75 Simriz 485

black

cross linking: peroxidic
FFKM

revision index
5

revision date
6/15/2015

page 1 / 2

Physical properties

	nominal range	typical values	
Density DIN EN ISO 1183-1, 23 °C	2.01 ±0.03	2.01	g/cm ³
Hardness ASTM D2240, Shore A, 23 °C	75 ±5	76	Shore
Modulus 100 %, ASTM D1414, 23 °C	---	5.7	MPa
Tensile strength ASTM D1414, 23 °C	> 12	18.5	MPa
Elongation at break ASTM D1414, 23 °C	> 140	195	%
Compression set ASTM D395, Slab B, 70 h, 200 °C, 25 %	< 30	23	%
Compression set ASTM D395, Slab B, 500 h, 200 °C, 25 %	---	31	%
Compression set ASTM D395, Slab B, 1000 h, 200 °C, 25 %	---	40	%
Compression set ASTM D395, Slab B, 70 h, 250 °C, 25 %	---	45	%
Low temperature test ASTM D1329, TR10	---	-4	°C
Temperature range	-15°C to 230°C short term: 260°C		

Declarations of conformity

This overview is purely informative and does not constitute a declaration of conformity (DoC). Please refer to the actual declaration of conformity (DoC) including the conditions and its validity period.

Country	Part	Remark	Expires
ADI Free		see certificate	see DoC
Info ROHS and ELV		EU 2000/53 (ELV) including EU 2011/65 and EU2015/863 (ROHS III)	see DoC

Freudenberg

Freudenberg FST GmbH
Technology&Innovation
Material Compliance

Telefon: -
Fax: -
Email: MaterialCompliance@fst.com



Material

75 Simriz 485

black

cross linking: peroxidic
FFKM

revision index
5

revision date
6/15/2015

page 2 / 2

No ASTM D2000 properties available

Standard material:

All-purpose, with excellence chemical resistance

The given values are based on a limited number of tests on standard test pieces (2mm sheets) produced in the laboratory. The data from finished parts can deviate from above values depending on the manufactories process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

Freudenberg

Freudenberg FST GmbH
Technology&Innovation
Material Compliance

Telefon: -
Fax: -
Email: MaterialCompliance@fst.com

