

Technical data sheet in accordance with ASTM

Material

80 FKM V801NBR

brown

cross linking: bisphenolically

revision index

1

revision date

7/29/2021

page

1 / 2

Physical properties

nominal range

typical values

Density

ASTM D297, 23 °C

2.16 ±0.02

2.16

g/cm³

Hardness

ASTM D2240, Shore A, 23 °C

80 ±5

77

Shore

Modulus

100 %, ASTM D412, C, 23 °C

MPa

Tensile strength

ASTM D412, C, 23 °C

> 10

12.4

MPa

Elongation at break

ASTM D412, C, 23 °C

> 150

206

%

Temperature range

-20°C to 200°C

Declarations of conformity

No data found!

Freudenberg

Freudenberg FST GmbH

Technology&Innovation

Material Compliance

Telefon: -

Fax: -

Email: MaterialCompliance@fst.com

Technical data sheet in accordance with ASTM

Material

80 FKM V801NBR

brown

cross linking: bisphenolically

revision index

revision date

1

7/29/2021

page

2 / 2

Tested after ASTM D 2000: M 2 HK 810 A1-10 B38 EF31 EO78 Z1

		nominal range	typical values
Hardness	Shore	80 ±5	77
Tensile strength	MPa	min. 10	12.4
Elongation at break	%	min. 150	206
A1-10 Change after aging in Air 70h/250°C			
Hardness	Shore A	10	4
Tensile strength	%	-25	8
Elongation at break	%	-25	-13
B38 Compression set 22h/200°C			
	%	50	12
EF31 Change after aging in Fuel C 70h/23°C			
Hardness	Shore	±5	-3
Tensile strength	%	-25	-21
Elongation at break	%	-20	15
Volume	%	0 to 10	4
EO78 Change after aging in Fluid No. 101 70h/200°C			
Hardness	Shore	-15 to 5	-9
Tensile strength	%	-40	-12
Elongation at break	%	-20	23
Volume	%	0 to 15	10
Z1 Specific Gravity ASTM D792			
	g/cc	---	2.16

The given values are based on a limited number of tests on standard test pieces (2mm sheets). The data from finished parts can deviate from above values depending on the manufacturing process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

Freudenberg

Freudenberg FST GmbH

Technology&Innovation

Material Compliance

Telefon: -

Fax: -

Email: MaterialCompliance@fst.com