

Material

80 NBR 177932

revision index

1

revision date

12/15/2021

page

1 / 2

Physical properties

	nominal range	typical values	
Density DIN EN ISO 1183-1	1.22 ±0.02	1.22	g/cm ³
Hardness DIN ISO 7619-1, Shore A	80 ±5	78	Shore
Modulus 100 %, DIN 53504	---	9.2	MPa
Tensile strength DIN 53504	> 11	15.1	MPa
Elongation at break DIN 53504, S2, 23 °C	> 250	280	%
Compression set DIN ISO 815, Slab B, 72 h, 100 °C	< 30	5.25	%
Low Temperature resistance ASTM D2137, Brittleness	< -30	-32	°C

Declarations of conformity

No data found!

Freudenberg

Freudenberg FST GmbH

Technology&Innovation

Material Compliance

Telefon: -

Fax: -

Email: MaterialCompliance@fst.com

Material

80 NBR 177932

revision index

1

revision date

12/15/2021

page

2 / 2

No ASTM D2000 properties available

The given values are based on a limited number of tests on standard test pieces (2mm sheets). The data from finished parts can deviate from above values depending on the manufacturing process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

Freudenberg

Freudenberg FST GmbH

Technology&Innovation

Material Compliance

Telefon: -

Fax: -

Email: MaterialCompliance@fst.com