

Material

85 EPDM 292

Version
 03

Released on
 05.04.2023

General Data

Colour: black
 Type of cross-linking: Peroxidic

Declaration of Compliance for - Food & Beverage - Pharmaceutical is available upon request for selected articles. Please contact your known sales contact or send an email to info@fst.com.

Physical Properties

	Nominal Range	Typical Value	
Density DIN EN ISO 1183-1, 23 °C	1.14 ±0.02	1.14	g/cm³
Hardness DIN ISO 48-4, Shore A, 23 °C	85 ±5	86	Shore
Modulus 100 %, DIN 53504, S2, 23 °C		16.8	MPa
Tensile strength DIN 53504, S2, 23 °C	>14	18	MPa
Elongation at break DIN 53504, S2, 23 °C	>110	114	%
Compression set DIN ISO 815, B, 24 h, 150 °C, 25 %	<30	11	%
Surface resistivity DIN EN 62631-3-1		4400	Ohm
Volume resistivity DIN EN 62631-3-2		76000	Ohm*c m

Temperature Range

static: -50 to 150 °C
 dynamic: -40 to 150 °C

This data sheet supersedes all previous versions. The content is subject to change without prior notice. The given values are based on a limited number of tests on standard test pieces (2mm sheets) produced in the laboratory. The data from finished parts can deviate from above values depending on the manufacturing process and the component geometry. The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

Print date: 20.10.2025
