



Material 85 NBR NB901803

Revision Index Revision Date

04 09.11.2022

General Data

Colour: black
Type of cross-linking: Sulfur

Declaration of Compliance for - DVGW Gas is available upon request for selected articles. Please contact your known sales contact or send an email to info@fst.com.

Physical Properties	Nominal Range	Typical Value	
Density CNS 5341-96, Method A	1.37 ±0.03	1.36	g/cm³
Hardness ASTM D2240-15, Shore A	90 ±5	86	Shore
Tensile strength ASTM D412-16		15.6	MPa
Elongation at break ASTM D412-16		175	%
Modulus 100 %, ASTM D412-16		10.9	MPa
Compression set ASTM D395-18, 22 h, 100 °C, button		6	%

The given values are based on a limited number of tests on standard test pieces (2mm sheets) produced in the laboratory. The data from finished parts can deviate from above values depending on the manufactories process and the component geometry. The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

Print date: 30.04.2025

Global Material Technology

Email: FIS.Compound.CRC@fst.com