

Material

85 AU 20991

violet

revision index

7

revision date

2/6/2024

page

1 / 2

Physical properties

| | nominal range | typical values | |
|---|---------------|----------------|-------------------|
| Density DIN EN ISO 1183-1, 23 °C | 1.14 ±0.02 | 1.14 | g/cm ³ |
| Hardness DIN ISO 7619-1, Shore A, 23 °C | 86 ±4 | 87 | Shore |
| Modulus 100 %, DIN 53504, S2, 23 °C | > 5 | 6.3 | MPa |
| Tensile strength DIN 53504, S2, 23 °C | > 48 | 58 | MPa |
| Elongation at break DIN 53504, S2, 23 °C | > 500 | 565 | % |
| Tear strength DIN ISO 34-1, B (b), 23 °C | --- | 45 | KN/m |
| Compression set DIN ISO 815, 24 h, 70 °C, 15 % | --- | 30 | % |
| Compression set DIN ISO 815, Slab B, 24 h, 100 °C, 15 % | --- | 44 | % |
| Low Temperature ISO 11357-2, DSC | --- | -50 | °C |
| Torsions pendulum test DIN EN ISO 6721-2A | --- | -38 | °C |
| Temperature range | -50°C to 90°C | | |

Declarations of conformity

This overview is purely informative and does not constitute a declaration of conformity (DoC). Please refer to the actual declaration of conformity (DoC) including the conditions and its validity period.

| Country | Part | Remark | Expires |
|-----------------------|------|---|---------|
| Conflict Mineral Free | | see certificate | see DoC |
| Info ROHS and ELV | | EU 2000/53 (ELV) including EU 2011/65 and EU2015/863 (ROHS III) | see DoC |

Freudenberg

Freudenberg FST GmbH

Technology&Innovation

Material Compliance

Telefon: -

Fax: -

Email: MaterialCompliance@fst.com

Material

85 AU 20991

violet

revision index

7

revision date

2/6/2024

page 2 / 2

No ASTM D2000 properties available

The given values are based on a limited number of tests on standard test pieces (2mm sheets) produced in the laboratory. The data from finished parts can deviate from above values depending on the manufacturing process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

Freudenberg

Freudenberg FST GmbH
Technology&Innovation
Material Compliance

Telefon: -

Fax: -

Email: MaterialCompliance@fst.com