

# Material

## 85 EPDM 292

black

cross linking: peroxidic

revision index

3

revision date

4/5/2023

page

1 / 3

### Physical properties

	nominal range	typical values	
<b>Density</b> DIN EN ISO 1183-1, 23 °C	1.14 ±0.02	1.14	g/cm <sup>3</sup>
<b>Hardness</b> DIN ISO 48-4, Shore A, 23 °C	85 ±5	86	Shore
<b>Modulus</b> 100 %, DIN 53504, S2, 23 °C	---	16.8	MPa
<b>Tensile strength</b> DIN 53504, S2, 23 °C	> 14	18	MPa
<b>Elongation at break</b> DIN 53504, S2, 23 °C	> 110	114	%
<b>Compression set</b> DIN ISO 815, Slab B, 24 h, 150 °C, 25 %	< 30	11	%
<b>Surface resistivity</b> DIN EN 62631-3-1	---	4400	Ohm
<b>Volume resistivity</b> DIN EN 62631-3-2	---	76000	Ohm*cm

### Temperature range

static: -50°C to 150°C  
dynamic: -40°C to 150°C

### Declarations of conformity

This overview is purely informative and does not constitute a declaration of conformity (DoC). Please refer to the actual declaration of conformity (DoC) including the conditions and its validity period.

	Country	Part	Remark	Expires
(EG) 1935/2004	EU		food	see DoC
(EG) 2023/2006 (GMP)	EU		(EG) 2023/2006 (GMP)	see DoC
3-A Sanitary	USA	Seals	Class II	12 / 2027
ADI Free			see certificate	see DoC
BFR XXI, Kat 4	DE		food	see DoC
BPA/Phthalate free			BPA/Phthalate free	see DoC
CMR Category 1A/1B free			see certificate	see DoC
Cytotoxicity USP chapter	-	Seals		11 / 2032

### Freudenberg

Freudenberg FST GmbH  
Technology&Innovation  
Material Compliance

Telefon: -  
Fax: -  
Email: MaterialCompliance@fst.com



# Material

## 85 EPDM 292

black

cross linking: peroxidic

### revision index

3

### revision date

4/5/2023

page 2 / 3

	Country	Part	Remark	Expires
87 & 88 (class VI)				
Decree of 21. March 1973	IT	O-Ring		09 / 2028
FDA	USA	Seals	§ 177.2600	see DoC
Info ROHS and ELV			EU 2000/53 (ELV) including EU 2011/65 and EU2015/863 (ROHS III)	see DoC
NSF 51	USA	Seals		see DoC

### Freudenberg

Freudenberg FST GmbH  
Technology&Innovation  
Material Compliance

Telefon: -  
Fax: -  
Email: [MaterialCompliance@fst.com](mailto:MaterialCompliance@fst.com)



## Material 85 EPDM 292

black

cross linking: peroxidic

**revision index**

3

**revision date**

4/5/2023

**page**

3 / 3

**No ASTM D2000 properties available**

Application in water and water vapor to max. 180 °C, for short time max. 210 °C

**Ozone resistance: to 1000 pphm (40 °C)**

The given values are based on a limited number of tests on standard test pieces (2mm sheets). The data from finished parts can deviate from above values depending on the manufactories process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

### Freudenberg

Freudenberg FST GmbH  
Technology&Innovation  
Material Compliance

Telefon: -  
Fax: -  
Email: [MaterialCompliance@fst.com](mailto:MaterialCompliance@fst.com)

