

revision index	revision date			
3	10/19/2016		page	1 / 2
Physical properties		nominal range	typical values	
Density		---	2.48	g/cm³
DIN EN ISO 1183-1, 23 °C				
Hardness		---	86	Shore
DIN ISO 7619-1, Shore A, 23 °C				
Micro hardness		---	81	IRHD
DIN ISO 48				
Modulus		---	10.4	MPa
100 %, DIN 53504, S2, 23 °C				
Tensile strength		---	10.1	MPa
DIN 53504, S2, 23 °C				
Elongation at break		---	110	%
DIN 53504, S2, 23 °C				
Tear strength		---	18.8	KN/m
DIN 53507, A, 23 °C				
Low Temperature		---	-12	°C
ISO 11357-2, DSC				

This overview is purely informative and does not constitute a declaration of conformity (DoC). Please refer to the actual declaration of conformity (DoC) including the conditions and its validity period.

	Country	Part	Remark	Expires
Info ROHS and ELV			EU 2000/53 (ELV) including EU 2011/65 and EU2015/863 (ROHS III)	see DoC

Freudenberg FST GmbH  
Technology&Innovation  
Material Compliance  
Telefon: -  
Fax: -  
Email: [MaterialCompliance@fst.com](mailto:MaterialCompliance@fst.com)

Email: [MaterialCompliance@fst.com](mailto:MaterialCompliance@fst.com)