

Technical data sheet in accordance with ASTM

Material

85 NBR N852W

black

cross linking: sulfur

revision index

1

revision date

9/24/2021

page

1 / 3

Physical properties

	nominal range	typical values	
Density CNS 5341-16	---	1.28	g/cm ³
Hardness ASTM D 2240, Shore A	85 ±5	84	Shore
Tensile strength ASTM D 412	> 14	20.5	MPa
Elongation at break ASTM D 412	> 125	167	%
Compression set ASTM D 395, Slab B, 22 h, 100 °C, max.	< 25	6.1	%

Declarations of conformity

No data found!

Freudenberg

Freudenberg FST GmbH

Technology&Innovation

Material Compliance

Telefon: -

Fax: -

Email: MaterialCompliance@fst.com

Technical data sheet in accordance with ASTM

Material

85 NBR N852W

black

cross linking: sulfur

revision index

revision date

1

9/24/2021

page

2 / 3

Tested after ASTM D 2000: M 7 BG 814 B14 EA14 EF11 EF21 EO14 EO34 Z1 Z2 Z3 Z4

		nominal range	typical values
Tensile strength	MPa	min. 14	20.5
Elongation at break	%	min. 125	167
A14 Change after aging in Air 70h/100°C			
Hardness	Shore A	---	3
Tensile strength	%	---	5
Elongation at break	%	---	-14
B14 Compression set 22h/100°C			
	%	25	6.1
EA14 Change after aging in Distilled water 70h/100°C			
Hardness	Shore A	±10	0
Volume	%	±15	4.1
EF11 Change after aging in Fuel A 70h/23°C			
Hardness	Shore A	±10	0
Tensile strength	%	-25	-3
Elongation at break	%	-25	-2
Volume	%	-5 to 10	2.1
EF21 Change after aging in Fuel B 70h/23°C			
Hardness	Shore A	0 to -30	-9
Tensile strength	%	-60	-30
Elongation at break	%	-60	-27
Volume	%	0 to 40	23.1
EO14 Change after aging in IRM 901 70h/100°C			
Hardness	Shore A	±5	0
Tensile strength	%	-25	-2

Freudenberg

Freudenberg FST GmbH

Technology&Innovation

Material Compliance

Telefon: -

Fax: -

Email: MaterialCompliance@fst.com

Technical data sheet in accordance with ASTM

Material

85 NBR N852W

black

cross linking: sulfur

revision index	revision date		page	3 / 3
1	9/24/2021			
	Elongation at break	%	-45	-10
	Volume	%	-10 to 5	-1.1
EO34 Change after aging in IRM 903 70h/100°C				
	Hardness	Shore A	-10 to 5	-6
	Tensile strength	%	-45	-3
	Elongation at break	%	-45	-12
	Volume	%	0 to 25	8.1
Z1	Hardness ASTM D2240, Shore A	Shore	85 ±5	84
Z2	Modulus 100 %, ASTM D412	MPa	---	13.97
Z3	Density	g/cm ³	---	1.28
Z4 Change after aging in Distilled water 70h/100°C				
	Hardness Shore A	Shore	±10	0
	Tensile strength	%	---	-2
	Elongation at break	%	---	-8
	volume change DIN ISO 1817	%	±15	4.1

The given values are based on a limited number of tests on standard test pieces (2mm sheets). The data from finished parts can deviate from above values depending on the manufactories process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

Freudenberg

Freudenberg FST GmbH

Technology&Innovation

Material Compliance

Telefon: -

Fax: -

Email: MaterialCompliance@fst.com