

Material
88 FKM 107725

black

revision index
5

revision date
3/22/2021

page 1 / 3

Physical properties

	nominal range	typical values	
Density DIN EN ISO 1183-1	1.99 ±0.03	1.99	g/cm ³
Hardness DIN ISO 7619-1	85 ±5	84	Shore
Rebound resilience DIN 53512	---	8	%
Tensile strength DIN 53504, S2	> 6.5	8	MPa
Elongation at break DIN 53504, S2	> 150	230	%

Declarations of conformity
No data found!

Freudenberg

Freudenberg FST GmbH
Technology&Innovation
Material Compliance

Telefon: -

Fax: -

Email: MaterialCompliance@fst.com

Material

88 FKM 107725

black

revision index	revision date	page	2 / 3
5	3/22/2021		

Tested after ASTM D 2000: M 3 HK 907 A1-10 B37 B38 EF31 EO78 Z1

		nominal range	typical values
Hardness	Shore	90 ±5	87
Tensile strength	MPa	min. 7	8.5
Elongation at break	%	min. 100	201
A1-10 Change after aging in Air 70h/250°C			
Hardness	Shore A	10	7
Tensile strength	%	-25	-18
Elongation at break	%	-25	-24
B37 Compression set 22h/175°C	%	30	20
B38 Compression set 22h/200°C	%	50	35
EF31 Change after aging in Fuel C 70h/23°C			
Hardness	Shore	±5	-5
Tensile strength	%	-25	-22
Elongation at break	%	-20	-10
Volume	%	0 to 10	5.2
EO78 Change after aging in Fluid No. 101 70h/200°C			
Hardness	Shore	-15 to 5	-10
Tensile strength	%	-40	-18
Elongation at break	%	-20	-3
Volume	%	0 to 15	10.6
Z1 Density DIN EN ISO 1183, 23 °C	g/cm ³	---	1.99

The given values are based on a limited number of tests on standard test pieces (2mm sheets) produced in the laboratory. The data from finished parts can deviate from above values depending on the manufacturing process and the component geometry.

Freudenberg

Freudenberg FST GmbH
 Technology&Innovation
 Material Compliance
 Telefon: -
 Fax: -
 Email: MaterialCompliance@fst.com

Material
88 FKM 107725

black

revision index

5

revision date

3/22/2021

page

3 / 3

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

FreudenbergFreudenberg FST GmbH
Technology&Innovation
Material Compliance

Telefon: -

Fax: -

Email: MaterialCompliance@fst.com